

HumiSeal® Stripper 1063 Technical Data Sheet

HumiSeal® Stripper 1063 is a non-acidic, non-destructive stripper that dissolves cured HumiSeal® polyurethane coatings without negatively affecting printed wiring board substrates or components. HumiSeal® Stripper 1063 is in full compliance with the RoHS Directive 2002/95/EC.

Typical Physical Properties of HumiSeal® Stripper 1063

Stripper	1063
Compatible HumiSeal® Coatings	1A27 & 1A33 Families
Relative Evaporating Rate (BuAc=1)	2.10
Specific Gravity	0.84 ± 0.01
Flash Point (°C) TCC	11.1
Shelf Life, DOM	12 months
Color	Clear

HumiSeal® Stripper 1063 is safe for use on copper, gold, silver or nickel plating, amine cured epoxies, diallyl phthalate, neoprene, phenolic resins, polyethylene, Teflon, Kynar and most vinyl coated wires. It will attack anhydride-cured epoxies and some magnetic wire coatings.

Directions for Use

- Immerse the assembly into HumiSeal® Stripper 1063
- Soak for 60 minutes
- Brush loose material from the assembly
- Clean the assembly with IPA, DI water or other qualified cleaning solution
- Inspect the assembly to ensure the coating has been completely removed
- Repeat the steps above if coating is still on the assembly
- Bake for a minimum of 30 minutes @ 60 - 65°C after the final cleaning process

A fully cured polyurethane coating of nominal thickness will typically dissolve readily within 60 minutes upon contact with HumiSeal® Stripper 1063. The use of heat is not required for use with HumiSeal® Stripper 1063, however the addition of heat between 40 – 45°C can aid in the efficiency of the stripping process. It is important to thoroughly clean the assembly after the conformal coating removal process. Following the cleaning process the assembly should be baked to remove residual moisture for a minimum of 30 minutes at 60 – 65°C.

Handling Precautions

HumiSeal® Stripper 1063 is flammable and the following standard safety precautions should be observed:

- Use only in well ventilated areas.
- Protective gloves and goggles should be worn.
- In case of prolonged skin contact, wash with water.
- In case of eye contact, flush with water followed by a diluted boric solution and contact physician.
- Avoid prolonged breathing of vapors.
- Unused portions of HumiSeal® products must be disposed of in compliance with all applicable environmental regulations.
- Consult the Material Safety Data Sheet (MSDS/SDS) for more specific product information.

Contact HumiSeal[®]

HumiSeal North America

201 Zeta Drive
Pittsburgh, PA 15238
USA
Tel: +1 412-828-1500
Toll Free (US only): 866-828-5470
sales@humiseal.com

HumiSeal Technical Center

295 University Avenue
Westwood, MA 02090
USA
Tel: +1 781-332-0734
Fax: +1 781-332-0703
techsupport@humiseal.com

HumiSeal Europe

505 Eskdale Road, IQ Winnersh
Berkshire RG41 5TU
UK
Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europesales@chasecorp.com

HumiSeal Europe Support

Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europetechsupport@chasecorp.com

HumiSeal S.A.R.L

4/6 Avenue Eiffel
78420 Carrieres-Sur-Seine
France
Tel: +33 (0) 1 30 09 86 86
Fax: +33 (0) 1 30 09 86 87
humiseal.sarl@chasecorp.com

HumiSeal Asian Support

Tel: 852-9451-6434
Fax: 852-2413-6289
asiatechsupport@humiseal.com

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.