




# STATFREE G2™ CONDUCTIVE RUBBER



**Conductive Rubber**

## Grounding & Cleaning

If the material is used on top of an already properly grounded ESD floor (or other substrate), [grounding hardware](#) may not be necessary. Where no properly grounded ESD floor is available, grounding hardware is required to provide a path-to-ground. Rg compliance verification measurements must be made with a [surface resistance meter](#).

See Tech Bulletin [TB-7000](#) for Rezto™ Surface & Mat Cleaner Application Instructions. See [PPE-5025](#) for guidelines regarding the maintenance and cleaning of ESD Mats.

## Limited Lifetime Warranty:

Desco Europe warrants for one year that Statfree® matting products will be free of defects in materials and workmanship and will guarantee dissipative/conductive mat properties for the life of the mat. Damage to matting caused by misuse of any kind, including using inappropriate cleaners is not covered by [Desco Europe Limited Warranty](#).

## RoHS 3, REACH, and Conflict Minerals Statement

See the Desco Europe RoHS 3, REACH, and Conflict Minerals Statement:  
<http://www.descoeurope.com/ROHS.aspx>

See the Desco Europe Limited Warranty:  
<http://descoeurope.com/Limited-Warranty.aspx>

See the Desco Europe Disclaimer:  
<http://desco.descoindustries.com/Disclaimer.aspx>

Specifications and procedures subject to change without notice.

## Specifications

**Standard Document**  
EN 61340-5-1

## Electrical Properties

Rp-p Resistance:

Rg Resistance:

## Typical Values

1 x 10<sup>4</sup> to < 1 x 10<sup>6</sup> Ohms

1 x 10<sup>4</sup> to < 1 x 10<sup>6</sup> Ohms

**Meets Requirements of:**  
Flooring

## Test Procedures/Method

IEC 61340-4-1

IEC 61340-4-1

## Physical Properties

Construction:

Thickness:

Colour:\*

Texture:\*

Weight:

Hardness:

Chemical Resistance:

Homogeneous, SBR, volume conductive rubber

0.060" (1.5mm)

Black

Low glare, light embossed texture, smooth

0.58 lbs/ft<sup>2</sup> (0.28g/cm<sup>2</sup>) nominal

70 Shore A (ASTM D-2240)

Resistance to degradation by inorganic acids, organic acids, reducing agents, aliphatic hydrocarbons, mineral oil, aldehydes, and amines

## Tolerances

Width:

Length:

± 0.250" (6.35mm)

± 0.250" (6.35mm) every 1 linear foot (0.3m) of running material.

Matting materials have a tendency to shrink slightly when first unrolled. In applications where length is critical, allow the material to relax for at least 4 hours before cutting to size. Always trim with a sharp knife or razor blade.

\*Colour and texture may vary between lots and mills

For product listings, [Click Here](#)



Made in the  
United States of America

## STATFREE G2™ FLOOR MAT, CONDUCTIVE, RUBBER, 0.060" (1.5mm)

# DESCOEUROPE

DESCO EUROPE  
2A DUNHAMS LANE, LETCHWORTH GARDEN CITY,  
HERTFORDSHIRE, SG6 1BE, UK  
PHONE: +44 (0) 1462 672005  
E-MAIL: [Service@DescoEurope.com](mailto:Service@DescoEurope.com), INTERNET: [DescoEurope.com](http://DescoEurope.com)

MATERIAL STATFREE G2™  
DRAWING PME-G2

**DATE:**  
July  
2017